


Originally developed as a "bearing bronze", C425 provides a low coefficient of friction plus a high work-hardening rate making the alloy an excellent choice for use in bearing surfaces. In addition this economical spring alloy provides maximum resistance to corrosion and excellent fatigue strength. Like other tin brasses C425 provides an excellent option for a wide range of applications and is typically found in automotive terminals and other electrical connectors.






Figure 1: Comparison of Tensile Strength , Electrical Conductivity and Stress Relaxation performance @ 1000hrs of select connector materials.

| Physical Properties | | | | | | | |
|---|----------------------------------|------------------------|--|--|--|--|--|
| | English Units | Metric Units | | | | | |
| Density | 0.317 lb/in ³ @ 68°F | 8.78 g/cm ³ | | | | | |
| Thermal Conductivity | 69 BTU-ft/ft ² -hr-ºF | 121 W/mºK | | | | | |
| Electrical Resistivity | 37.0 ohm circ mils/ft | 6.20 microhm-cm | | | | | |
| Electrical Conductivity (annealed) | 28% IACS* | 0.161 megamho/cm | | | | | |
| Modulus of Elasticity | 16,000,000 psi | 110 kN/mm ² | | | | | |
| Thermal Capacity(Specific Heat) | 0.090 Btu/lb/F° @ 68°F | 0.090 cal/gm/Cº @ 20ºC | | | | | |
| Coeff. Of Thermal Expansion | _ | | | | | | |
| 68-572°F (20-300°C) | 10.2 PPM/°F | 18.36 PPM/°C | | | | | |
| *International Annealed Copper Standard | | • | | | | | |

| Mechanical Properties | | | | | | | | | | |
|-----------------------|------------------|-------------------|-----------------------------|-------------------|---------------------------|---------------------------------|-----|--|--|--|
| Temper ¹ | Tensile Strength | | Yield Strength ² | | % Elongation ² | Typical 90° Bend Formability | | | | |
| | ksi | N/mm ² | ksi | N/mm ² | | GW/BW ³ | | | | |
| Annealed | 41-47 | 285-325 | 17 | 115 | 48 | - | - | | | |
| 1/4 Hard | 49-59 | 340-405 | 37 | 255 | 35 | - | _ | | | |
| 1/2 Hard | 57-69 | 395-475 | 58 | 400 | 20 | - | _ | | | |
| 3/4 Hard | 62-74 | 425-510 | 64 | 440 | 15 | - | 0.5 | | | |
| Hard | 70-82 | 485-565 | 72 | 495 | 9 | 0.3 | 1.5 | | | |
| Extra Hard | 76-88 | 525-605 | 79 | 545 | 6 | 0.5 | 2.0 | | | |
| Spring Hard | 84-94 | 580-650 | 90 | 620 | 4 | 8.0 | 3.0 | | | |
| Extra Spring | 92 min | 635 min | 87min | 600 min | 2 max | | | | | |

¹ Mechanical properties subject to change. All tempers listed are made to a Tensile Strength specification unless otherwise noted.

² Nominal Values ³ DATA FOR REFERENCE ONLY. R/T = Bend Radius/Material Thickness <0.016" (0.4mm) thick, 11/16 (17.5mm) wide.